

LANOSEAL LS773

TECHNICAL SPECIFICATION

Characteristic	Test Method	Unit of Measurement	Specification	Typical Result
Appearance	ASTM D4176	N/A	Clear, bright	Free of particulates
Colour	ASTM D1500	N/A	9.0 min.	> 10
Relative Density	ASTM D4052	kg/m	0.85 - 0.90	0.87
Viscosity (@ 25°C)	ASTM D1200	cSt	25.0 – 40.0	30.0
Flash Point	Abel	°C	> 93	80
Total Acid Number	ASTM D974	N/A	< 10	7.5
NLGI Classification	ASTM D217	INDEX	000 - 6	000
Food Grade	FDA	H1	Clear, bright	H1
Metals	ICP			
Iron		ppm	< 10	< 1
Zinc		ppm	< 10	5
Calcium		ppm	< 20	18
Magnesium		ppm	< 10	< 1
Phosphorus		ppm	Report	2
Aluminium		ppm	< 10	5
Sodium		%	< 10	5
Sulfur		%	-	-
Ash		%	-	-
Chloride		ppm	< 0	< 0
Water Content	Karl-Fisher	%	< 2 max.	0.2
Copper Corrosion	ASTM D130	N/A	1 max.	1a

The information in this document is given in good faith and is true and accurate to the best of company knowledge. No warranty or guarantee (e.g. on suitability for a formulation) is expressed or implied. This document reflects legislative knowledge at the time of preparation, and may be subject to change in the future. It is the user's responsibility to determine the suitability for use of the information presented, and to ensure compliance, at any time. No warranty or freedom is given regarding the industrial property rights of Lantos Coatings Pte Ltd or third parties. No responsibility or liability for any consequences arising from the use of this document can be accepted. This version replaces earlier versions. The information in this document cannot be reproduced in part or whole without the express permission of Lantos Coatings Pte Ltd. Copyright © 2018.